

Review

Structural characterization and rheological properties of a gel-like β -D-glucan from *Pholiota nameko*



Vanessa Sovrani^{a,1}, Liana Inara de Jesus^{a,1}, Fernanda Fogagnoli Simas-Tosin^b,
Fhernanda Ribeiro Smiderle^a, Marcello Iacomini^{a,*}

^a Department of Biochemistry and Molecular Biology, Federal University of Parana, CP 19046 Curitiba, PR, Brazil

^b Department of Cell Biology, Federal University of Parana, CP 19031 Curitiba, PR, Brazil

ARTICLE INFO

Article history:

Received 17 February 2017

Received in revised form 23 March 2017

Accepted 28 March 2017

Available online 31 March 2017

Keywords:

Pholiota nameko

Structural characterization

β -D-Glucan

Rheology

ABSTRACT

A crude fraction (SCW) was extracted with cold water from *Pholiota nameko* and showed mannose (24.1%), galactose (44.9%) and glucose (31%). Purification procedures resulted in a polysaccharide fraction (bG-PN), that showed only glucose. NMR and methylation analyses of bG-PN indicated a β -D-glucan-(1 $\rightarrow$ 3)-linked, substituted at O-6 by β -D-Glcp or (1 $\rightarrow$ 6)-linked β -D-Glcp side chains. Rheological studies of crude and purified fractions at the same concentration showed similar shear-thinning behavior and gel-like structure which indicates no need to isolate the polymer to achieve some desirable rheological properties. SCW (at 1% and 2%) and bG-PN (at 2%) presented thermal stability during heating and cooling, suggesting that the physical structure of gels (SCW and bG-PN at 2%) and viscoelastic fluid (SCW at 1%) formed were not altered in the tested temperature range. Our results suggest that *P. nameko* β -D-glucans can be applied in different food preparations as thickener or gelling agents modifying their rheological properties.

© 2017 Published by Elsevier Ltd.

Contents

1. Introduction	2
2. Material and methods	2
2.1. Fungal material	2
2.2. Extraction and purification	2
2.3. Analysis of monosaccharide composition by GC-MS	2
2.4. Methylation analysis	3
2.5. Controlled Smith degradation of β -D-glucan (bG-PN)	3
2.6. Nuclear magnetic resonance	3
2.7. Rheological measurements	3
3. Results and discussion	3
3.1. Preparation of polysaccharide extracts and isolation of β -D-glucan	3
3.2. Chemical composition of SCW fraction and characterization of β -D-glucan	3
3.3. Rheological characterization of SCW and β -D-Glucan fractions	4
4. Conclusion	7
Acknowledgments	7
Appendix A. Supplementary data	7
References	7

* Corresponding author.

E-mail address: iacomini@ufpr.br (M. Iacomini).

¹ The authors (VS, LIdeJ) contributed equally to this article.

1. Introduction

Edible mushrooms have been considered for many years as functional foods due to their high nutritional value (Ren, Perera, & Hemar, 2012). They present an attractive chemical composition, being rich in proteins, carbohydrates, fibers, vitamins and unsaturated fatty acids (Wani, Bodha, & Wani, 2010). Mushrooms have showed a great interest in biomedical area due to the presence of bioactive substances, including polysaccharides (Zhao, Wang, & Lu, 2009). *Pholiota nameko* is a well known edible mushroom rich in biological compounds, being extensively cultivated to be used as food and as traditional medicine in China and Japan (Neda, 2008; Zhang et al., 2014).

Studies showed that *P. nameko* polysaccharides demonstrated strong anti-inflammatory activity in rodents through paw edema model (Li, Lu, Zhang, Lu, & Liu, 2008) and hypolipidemic effect after orally treatment in hyperlipidemic rats (Li, Zhang, & Ma, 2010). Furthermore, this mushroom can be useful for food industry to design supplements due to its potential as prebiotic (Rodrigues et al., 2017). Fungal polysaccharides comprise a large group of polymers with pharmaceutical and biotechnological applications and such properties are closely related to their chemical structures (Bot, Smorenburg, Vreeker, Pâques, & Clark, 2001; Ruthes, Smiderle, & Iacomini, 2015). The most studied class of polysaccharides present in edible mushrooms are the β -D-glucans which frequently consist of a backbone composed of β -(1 $\rightarrow$ 3)-linked glucopyranose, partially substituted at O-6 position by glucopyranose units (Ren, Reynisson, Perera, & Hemar, 2013; Synytsya & Novak, 2014).

Mushroom nutritional values associated with their therapeutic benefits stimulate the application of such organisms or their extracts in food industry as additives, supplements and emulsifiers (Liu et al., 2016; Xu, Xu, Zhang, & Zhang, 2008; Xu, Zhang, Liu, Sun, & Wang, 2016). β -D-Glucans can present special physicochemical properties such as gelling capability, which might be employed in food, pharmaceutical and cosmetic industry (Laroche & Michaud, 2007). The determination of their rheological characteristics is helpful to predict gelation, thickening and emulsification properties. β -D-Glucans are abundant polysaccharides in edible mushrooms and have potential to increase water viscosity and provide desirable appearance and texture for food products (Bot et al., 2001; Synytsya & Novak, 2014). The viscosity promoted by such molecules in solution is related to their molecular weight, chemical structure, concentration and food matrix (Zhu, Bin, Bian, & Xu, 2015).

Few reports have mentioned some food industry applications using β -glucan, such as rice noodles prepared with β -glucan-rich fractions from *L. edodes* (Heo et al., 2013); and wheat flour mixture containing β -glucan-enriched material from the same mushroom to prepare cakes (Kim et al., 2011). In both cases, the addition of mushroom β -glucans enhanced the quality of the products by improving texture characteristics and increasing the fiber content.

Observing the potential use of mushroom β -glucan-rich fractions for food industry, this study aimed to isolate, purify and structurally characterize a gel-like β -D-glucan from *Pholiota nameko*, including studies on rheological properties of the crude and purified fractions.

2. Material and methods

2.1. Fungal material

Pholiota nameko was kindly provided by the company Nayumi Cogumelos, located in the city of Mogi das Cruzes, São Paulo, Brazil.




Fig. 1. Scheme of extraction and purification of β -D-glucan obtained from fruiting bodies of *Pholiota nameko*.

2.2. Extraction and purification

Pholiota nameko (PN) (2.5 kg) was freeze dried until total dryness (226.0 g) and milled in a blender (Fig. 1). The apolar compounds were extracted using a chloroform-methanol solution (2:1 v/v) at 60 °C for 5 h (3 times). Subsequently, the residue was dried and submitted to sequential aqueous extractions at room temperature (23 °C) under mechanical stirring for 6 h (3 times). The aqueous extract was concentrated under reduced pressure and the polysaccharide was precipitated with ethanol (3:1 v/v). The ethanolic solution was centrifuged at 8500 rpm at 10 °C for 20 min and the precipitate was dialyzed (12–14 kDa M_r cut-off membrane) against tap water for 24 h and freeze dried.

The resultant fraction (CW; 37.4 g) was submitted to freeze-thawing process (Gorin & Iacomini, 1984). This method consists of solubilizing the sample in small volume of distilled water followed by freeze and slowly thawing at room temperature (23 °C) until the formation of precipitates. The soluble fraction (SCW; 17.9 g) was separated from the insoluble one by centrifugation (8500 rpm, 4 °C, 20 min) and treated with Fehling solution (Jones & Stoodley, 1965). The fraction (FSCW; 1.2 g) which did not complex with Cu^{2+} ions was recovered after centrifugation (8500 rpm, 4 °C, 20 min) and separated from the insoluble Cu^{2+} complex, which was not used in this study.

The obtained fractions were neutralized with HOAc, dialyzed against tap water for 48 h (12–14 kDa M_r cut-off membrane) and deionized on a cationic resin ion exchange and then freeze dried. The FSCW fraction was submitted to another freeze-thawing process and centrifuged (8500 rpm, 4 °C, 20 min): resulting in a soluble fraction (not used in this study) and a gel fraction (bG-PN; 0.52 g), that was used for the chemical and rheological analysis.

2.3. Analysis of monosaccharide composition by GC–MS

Aliquots of polysaccharide fractions (1.0 mg) were hydrolyzed with 2 M TFA for 8 h at 100 °C following the method of Sassaki et al. (2008). The acid was removed by evaporation to dryness. The hydrolyzed products were dissolved in distilled water (100 μL) and 1 mg of NaBH_4 was added. The solution was held overnight in room temperature (23 °C) to reduce aldoses into alditols, neutralized with HOAc and later evaporated to dryness. The residue was removed following the addition of methanol (2 times) under a compressed air stream in a fume hood. The samples were acetylated with pyridine- Ac_2O (200 μL ; 1:1, v/v), heated for

30 min at 100 °C. The resulting alditol acetates were extracted with chloroform and analyzed by gas chromatography–mass spectrometry (GC–MS) using a Varian model CP-3800 gas chromatograph coupled to an Ion-Trap 4000 mass spectrometer, with a VF5 column (30 m × 0.25 mm i.d.) programmed from 100 to 280 °C at 10 °C/3 min, with He as carrier gas. The alditol acetates were identified by their typical retention times and electron impact profiles.

2.4. Methylation analysis

Per-*O*-methylation of purified polysaccharide (bG-PN) fraction was carried out using NaOH–Me₂SO–MeI according to Ciucanu and Kerek (1984). After isolation of the products by neutralization (HOAc), dialysis, and evaporation, the methylation process was repeated. The per-*O*-methylated products were submitted to methanolysis with MeOH–HCl 3 N (1 mL) for 2 h at 80 °C (Jansson, Kenne, Liedgren, Lindberg, & Lonngren, 1976) followed by hydrolysis using 2 N sulphuric acid (1 mL) for 16 h at 100 °C. The sample was reduced with NaBD₄ and acetylated to give a mixture of partially *O*-methylated alditol acetates, which was analyzed by GC–MS. Partially *O*-methylated alditol acetates were identified from *m/z* by comparing their positive ions with standards and expressed as a relative percentage of each component.

2.5. Controlled Smith degradation of β-D-glucan (bG-PN)

The purified fraction (bG-PN; 50 mg) was oxidized with 0.05 M aqueous NaIO₄ (20 mL) at room temperature (23 °C) protected from light for 72 h. Ethylene glycol was added to stop the reaction, the material was dialyzed (2 kDa M_r cut-off membrane) and the resulting polyaldehyde was reduced with NaBH₄ for 12 h, neutralized with HOAc, dialyzed and concentrated to 50 mL (Goldstein, Hay, Lewis, & Smith, 2005). The residue was submitted to partial hydrolysis with TFA, pH 2.0, for 30 min at 100 °C and dialysis (2 kDa M_r cut-off membrane). The final solution was freeze dried the material resistant to oxidation was analyzed by ¹³C NMR spectroscopy.

2.6. Nuclear magnetic resonance

¹³C- and HSQC NMR spectra were obtained using a 400 MHz Bruker model Avance III spectrometer with a 5 mm inverse probe. The analyses were performed at 70 °C and polysaccharide samples (40 mg) were dissolved in Me₂SO-*d*₆. Chemical shifts are expressed in ppm (δ) relative to Me₂SO-*d*₆ ¹³C and ¹H signals at δ 39.40 and 2.40, respectively.

2.7. Rheological measurements

Rheological analysis were made on crude fraction SCW (at 1% and 2% w/w), that presented 48.4% yield and on the isolated β-D-glucan fraction (bG-PN), at 2% (w/w) due its low yield (1.4%). Samples were solubilized in distilled water being maintained under magnetic stirring for 5 days at 70 °C and rest during 20 min before analyses. Rheological measurements were carried out using a HAAKE MARS II rheometer (Thermo Fisher Scientific, Karlsruhe, Germany), at 25 °C with a cone-plate (C60/2° TiL) measurement system. A 1 mm measurement gap was used. The temperature was controlled by a circulating water bath (DC5, Haake) coupled to a Peltier temperature control device (TC 81, Haake). During measurements on temperature variation, the system containing sample was covered with a sample hood (POM 222-1903) to prevent water evaporation. Before all rheological measurements, samples were maintained on the plate for 300 s, in order to allow temperature equilibrium. Viscosity curves were obtained in the CR mode (controlled shear rate) by applying an increasing shear rate (0.005–500 s^{−1}) during 300 s. Viscoelastic behavior of samples were

Table 1

Monosaccharide composition of fractions obtained from *Pholiota nameko*.

Fractions	Monosaccharide Composition (%) ^a		
	Man	Gal	Glc
CW	14.1	6.3	79.6
SCW	24.1	44.9	31.0
bG-PN	–	–	100.0

^a % of peak area relative to total peak areas, determined by GC–MS.

evaluated using frequency sweeps (0.02–10 Hz) with strain of 1%. On thermostability studies, temperature sweeps were performed by heating (5–60 °C) and subsequent cooling (60–5 °C) the samples at a rate of 2 °C/min, at a frequency of 1 Hz and strain of 1%. The software RheoWin 4 Data Manager was employed to obtain the rheological parameters. All the analyses were performed in triplicates and graphs show the mean values and their corresponding standard error of the mean (SEM).

3. Results and discussion

3.1. Preparation of polysaccharide extracts and isolation of β-D-glucan

Polysaccharide fractions were obtained from *Pholiota nameko* fruiting bodies after successive cold water extractions as explained above (Section 2.2). Table 1 presents the monosaccharide composition of each fraction obtained over the purification process.

All fractions analyzed presented mannose, galactose and glucose, being this last monosaccharide the most abundant in CW (79.6%) and bG-PN (100%) fractions. The composition observed for CW and SCW indicated the presence of a mixture containing a D-glucan and an heteropolysaccharide composed of mannose and galactose as observed in previous reports that isolated mannogalactans from basidiomycetes (Smiderle, Olsen, Carbonero, Baggio et al., 2008; Smiderle, Olsen, Carbonero, Marcon et al., 2008; Silveira et al., 2015). Fehling solution treatment was effective to separate the D-glucan from the other heteropolysaccharide, as confirmed by the monosaccharide composition of bG-PN (Table 1).

3.2. Chemical composition of SCW fraction and characterization of β-D-glucan

The SCW fraction presented a mixture of monosaccharide components (Table 1) and was submitted to treatment with Fehling solution and freeze-thawing purification process giving rise to bG-PN fraction. NMR spectra of crude and purified fractions are shown in Fig. 2. ¹³C NMR spectrum of the crude extract SCW (Fig. 2A) indicated a mixture of polysaccharides due to the presence of various anomeric signals.

The main C-1 signals that correspond to β-D-Glcp (δ 102.8), β-D-Manp (δ 101.5), α-D-Glcp (δ 100.2) and α-D-Galp (δ 98.8) were identified by comparison with previous reports (Rosado et al., 2003; Smiderle et al., 2006, 2010). The signal at δ 79.1 arises from O-4 substitution of α-D-Glcp residues characteristic of glycogen-like polysaccharides, which are normally encountered in mushrooms (Smiderle et al., 2010; Stanek, Falk, & Huber, 1998). The presence of mannogalactans in SCW fraction was confirmed by the signals at δ 76.8 and δ 66.9, corresponding to O-2 and O-6 substitutions of α-D-Galp residues (Silveira et al., 2015). Furthermore, signals at δ 85.8; 86.0; and 86.4 indicated O-3 substitution of β-D-Glcp residues (Moreno et al., 2016).

Methylation analysis of bG-PN showed the presence of 2,3,4,6-Me₄-Glcp (27%); 2,4,6-Me₃-Glcp (30%); 2,3,4-Me₃-Glcp (16%); and 2,4-Me₂-Glcp (27%) derivatives. These data indicate that bG-PN presents a backbone composed of Glcp-(1 → 3)-linked, highly




Fig. 2. ^{13}C NMR spectra of SCW (A) and bG-PN (β -D-glucan) (B) fractions in $\text{Me}_2\text{SO}-d_6$ at 70°C (chemical shifts are expressed in δ ppm).

substituted at O-6 by Glcp residues and/or side chains of Glcp- $(1 \rightarrow 6)$ -linked. A similar D-glucan, with the same proportion of side-branches was isolated previously from *Cookeina tricholoma* by alkaline extraction (Moreno et al., 2016). Interestingly, in the present study, the D-glucan was easily extracted by water.

To confirm methylation results, bG-PN was analyzed by NMR spectroscopy (Figs. 2B and 3).

The ^{13}C NMR spectrum contained only one anomeric signal at δ 102.8 (Fig. 2B), while it was observed two distinct signals (C-1/H-1) in HSQC experiment, one at δ 102.4/4.12 corresponding to non-reducing end-units, and another at δ 102.4/4.41 from 3-O- and 3,6-di-O-substituted residues. The β -configuration was confirmed by low frequency H-1 (δ 4.12 and 4.41) and high-frequency C-1 signals (δ 102.4) (Hall & Johnson, 1969). The glycosidic linkages suggested by the methylation analyses were confirmed by the presence of 3-O-substitution signals at δ 86.5, 86.1 and 85.8 (Figs. 2B and 3) and 6-O-substitution signals at δ 68.3 (Fig. 2B), which appeared as doublet in HSQC spectrum at δ 68.1; 3.96/3.41 (Fig. 3) and was confirmed by RMN- ^{13}C -DEPT experiment (data not shown). Non-substituted C-6 signals were also observed and are assigned at δ 60.7 (Fig. 2B), 60.5/3.58 and 60.6/3.36 (Fig. 3) (Carbonero et al., 2012). The other signals in HSQC spectrum at δ 72.3/3.20; 68.1/3.15; 75.9/3.08 are attributed to C2/H2, C4/H4, and C5/H5 respectively, of β -D-Glcp- $(1 \rightarrow 3)$ -linked main chain. Similar signals relative to mushroom β -D-glucans were observed by Carbonero et al. (2006), Ruthes et al. (2013) and Moreno et al. (2016).

The main chain of the isolated β -D-glucan (bG-PN) was confirmed after performing a controlled Smith degradation that consists of NaIO_4 oxidation followed by mild acid hydrolysis. Only $(1 \rightarrow 3)$ -linked residues are resistant and all branching residues were totally oxidized by this procedure and after analyzing the

residual product by ^{13}C NMR, six intense signals were observed (Fig. 4). It proved to be a linear $(1 \rightarrow 3)$ -linked β -D-glucan with six typical signals at δ 102.8; 86.1; 76.3; 72.8; 68.3 and 60.7 ppm corresponding to C-1, C-3, C-5, C-2, C-4, and C-6, respectively (Gorin, 1981).

The results obtained by the chemical analyses are in agreement and confirmed the presence of a β -D-glucan with a main chain $(1 \rightarrow 3)$ -linked and highly substituted at O-6 by non-reducing β -D-Glcp or β -D-Glcp- $(1 \rightarrow 6)$ -linked side chains.

Similar β -D-glucans from *Pleurotus florida* (Rout, Mondal, Chakraborty, Pramanik, & Islam, 2005), *Pleurotus pulmonarius* (Smiderle, Olsen, Carbonero, Baggio et al., 2008) and *Cantharellus cibarius* (Nyman, Achmann, Rise, Balance, & Samuelsen, 2016) have been studied. Rodrigues et al. (2015) observed evidences of β -glucans, α -glucans and glucan-protein complexes by FTIR-ATR in five species of mushrooms including *P. nameko*. However, the chemical characterization of such molecules had not been reported. Studies on biological activities of crude polysaccharide extracts from genus *Pholiota* are commonly found, although there is a lack of information relating the chemical structure of such polymers with their biological effects or rheological properties (Li et al., 2008, 2010). A purified $(1 \rightarrow 3)$, $(1 \rightarrow 6)$ - β -D-glucan from *P. nameko* fungi has not been reported up to this date.

3.3. Rheological characterization of SCW and β -D-Glucan fractions

High degree of polysaccharide branching promotes higher interaction between water and polysaccharides by hydrogen bonds. Such inter- and intramolecular interactions may also influence solution behavior by increasing viscosity or forming gels (Yalpani &




Fig. 3. HSQC NMR spectrum of bG-PN in $\text{Me}_2\text{SO}-d_6$ at 70°C (chemical shifts are expressed in δ ppm).




Fig. 4. ^{13}C NMR spectrum of partially degraded glucan from *Pholiota nameko* in $\text{Me}_2\text{SO}-d_6$ at 70°C (chemical shifts are expressed in δ ppm).

Hall, 1984). Fraction SCW and the highly branched β -D-glucan isolated from *P. nameko* showed gelling appearance, therefore their rheological properties were evaluated.

The flow behavior of SCW fraction (at 1% and 2% w/w) was compared with the behavior of isolated β -D-glucan (at 2% w/w) (Fig. 5).

The apparent viscosity of the first one (SCW) was concentration dependent, as zero shear viscosity value increase when the polymer concentration rises. The viscosity observed for 1% SCW

dispersion at a shear rate of 0.01 s^{-1} was 4.1 Pas and increased to 49.5 Pas at 2% of concentration. It was observed that at higher concentrations there is more intermolecular connections promoting “junction zones”, which limit movement and stretching of polymers in solution and, consequently increase viscosity (Freitas et al., 2009). SCW aqueous dispersions showed lower viscosity than those observed for aqueous extract from *Flammulina velutipes* (Du et al., 2016) and *Auricularia auricular-judae* (Bao et al., 2016). These could be related to the composition of the extracts, considering that all of




Fig. 5. Flow (empty symbols) and viscosity (full symbols) curves of aqueous SCW fraction at 1% and 2% and aqueous bG-PN fraction at 2%.

them were composed by galactose, mannose and glucose in different proportions. The crude fraction SCW presented higher amounts of galactose (44.9%) in comparison to *A. auricular-judae* and *F. velutipes* fractions, that contained 5.4% (Bao et al., 2016) and 12% of galactose residues (Yang et al., 2012), respectively.

Both tested concentrations of SCW fraction (1% and 2% w/w) showed shear-thinning behavior, as there was an increase of the shear stress and a pronounced decrease of their viscosities, especially after 0.05 s^{-1} , with the increasing of the shear rate (Fig. 5). This is a common behavior of polysaccharide dispersions, where disordered polysaccharides seem to align or deform along the flow direction, decreasing the dispersion viscosity (Lapasin & Prich, 1995). Such behavior was identified for other polysaccharides from edible mushrooms as *F. velutipes* (Du et al., 2016), floral mushrooms (Xu et al., 2016), *A. auricular-judae* (Bao et al., 2016), and *Ganoderma lucidum* (Liu et al., 2016).

The flow and viscosity curves of fraction bG-PN at 2% (Fig. 5) were very similar with those observed for SCW at the same concentration, for all tested shear rates, suggesting that it is not necessary to completely purify the β -D-glucan to obtain the desirable viscosity. This result is interesting for the application in industry, which requires less purification steps to avoid unnecessary expenses. Besides, SCW yield was 34 times higher than bG-PN. The purified β -D-glucan from *P. nameko* formed less viscous aqueous dispersion than those isolated from floral mushrooms (Xu et al., 2016) and *G. lucidum* (Liu et al., 2016), although all of them showed shear-thinning behaviors. The fraction bG-PN (at 2%) presented viscosity of 3.5 Pa s at 1 s^{-1} while that from floral mushrooms cultivated in Huangshan Mountain have similar viscosity at half of concentration (Xu et al., 2016). Initial viscosity of bG-PN (at 2%) at first Newtonian plateau, at 0.01 s^{-1} , was 38.4 Pa s , while β -D-glucan from *G. lucidum* showed almost 150 Pa s at the same shear rate (Liu et al., 2016). β -D-Glucan from *P. nameko* showed a highly branched structure, containing longer side chains in comparison to β -D-glucans from floral mushrooms (Xu et al., 2016) and *G. lucidum* (Liu et al., 2016), that present only non-reducing end units of Glcp as branches. Such chemical characteristics may be responsible for the differences observed on viscosity of the three β -D-glucans.

The viscoelastic behaviors of fraction SCW (at 1% and 2% w/w) and isolated β -D-glucan (at 2% w/w) at 25°C are shown in Fig. 6.

G' and G'' of SCW at 1% were crossed-over at low frequency ($<0.05 \text{ Hz}$) characterizing it as concentrated solution and entangled systems (Clark & Ross-Murphy, 1987). When the concentration reached 2% (w/w), SCW showed a gel-like behavior with G' higher than G'' , both slightly frequency dependent, in all tested frequency range. The increase of concentration promoted the formation of more entanglements and junction points between the polymer




Fig. 6. Frequency sweeps at 25°C of fractions SCW at 1% and 2% and bG-PN at 2%. Elastic modulus (G') is represented by full symbols while viscous modulus (G'') by open symbols. Fixed strain of 1%.




Fig. 7. Elastic (G' , full symbols) and viscous moduli (G'' , open symbols) of fractions SCW (at 1% and 2%) and bG-PN (at 2%) as a function of temperature. Fixed frequency at 1 Hz and strain of 1%.

chains resulting in formation of a gel network (Brito, Sierakowski, Reicher, Feitosa, & Paula, 2005). The gel-like behavior was also noticed in aqueous extract from mushroom *A. auricular-judae* (named AP) at 0.5%, 1%, and 2%, and gel strength increased with increment of AP concentration (Bao et al., 2016). Our results showed that bG-PN (2% w/w) has similar gel-like behavior than that from aqueous extract SCW at the same concentration (Fig. 6). The β -D-glucan from *P. nameko* formed lower strength gel than that from *G. lucidum*, as G' and G'' values of bG-PN at 2% were comparable with those from *G. lucidum* at 1%, at the same temperature (Liu et al., 2016). In contrast, β -D-glucan isolated from floral mushrooms (Xu et al., 2016) (at 1%) did not form gel at 25°C (Xu et al., 2016).

With the aim of investigating thermal stability of SCW and bG-PN, dispersions were heated (from 5 to 60°C) and cooled (from 60 to 5°C) and their viscoelastic moduli were determined. SCW (at 1% and 2%) and bG-PN (at 2%) showed strong thermal stability over the temperature course (Fig. 7). During heating and cooling, G' and G'' reached almost the same values as the initial temperatures, suggesting that the temperatures tested did not affect the physical structure of gels and viscoelastic fluids formed by both samples.

At the temperature ramps, bG-PN (2% w/w) showed higher G' and G'' values than those observed for SCW fraction at the same concentration (Fig. 7). This behavior was different from that observed at frequency sweeps suggesting that at 5°C , there were more intra- and intermolecular associations between the isolated β -D-glucan molecules, resulting in more junction zones and consequently in more strength gel than that formed at 25°C . The β -D-glucan (bG-PN) gel showed to be thermal stable, without strength loss, during the temperature ramp tested.

4. Conclusion

Polysaccharide extracts from *P. nameko* were obtained by cold water extractions and a highly branched glucan was purified and chemically characterized. Its backbone was composed of (1 → 3)-linked β-D-Glcp units, being 27% substituted at O-6 by single units of β-D-Glcp or (1 → 6)-linked β-D-Glcp side chains. The crude extract (SCW) and purified β-D-glucan (bG-PN) showed similar non-Newtonian shear-thinning behavior, and viscosity of SCW fraction was higher when there was an increase in its concentration. SCW and bG-PN (at 2%) showed gel-like behavior and were thermal stable between the range of 5–60 °C. Such characteristics suggested a potential application of *P. nameko* fractions to increase thickness of food products and also to improve resistance of products submitted to different temperatures during its processing, storage and/or transport. The shear-thinning behavior and gel-like structure of SCW and bG-PN fractions at 25 °C were similar at the same concentration which suggested there is no need to purify the β-D-glucan to obtain some desirable rheological properties. The results obtained indicate a potential use of β-D-glucan-rich fractions from *P. nameko* in food industry as thickening agents to improve desirable characteristics of food products associated with other therapeutic benefits that are attributed to β-D-glucans.

Acknowledgments

The authors would like to thank the Brazilian funding agencies Conselho Nacional de Desenvolvimento Científico e Tecnológico (CNPq), Coordenação de Aperfeiçoamento de Pessoal de Nível Superior (CAPES) and Fundação Araucária for the financial support.

Appendix A. Supplementary data

Supplementary data associated with this article can be found, in the online version, at <http://dx.doi.org/10.1016/j.carbpol.2017.03.093>.

References

- Bao, H., You, S. G., Cao, L., Zhou, R., Wang, Q., & Cui, S. W. (2016). Chemical and rheological properties of polysaccharides from fruit body of *Auricularia auricular-judae*. *Food Hydrocolloids*, 57, 30–37. <http://dx.doi.org/10.1016/j.foodhyd.2015.12.031>
- Bot, A., Smorenburg, H. E., Vreeker, R., Pâques, M., & Clark, A. H. (2001). Melting behaviour of schizophyllan extracellular polysaccharide gels in the temperature range between 5 and 20 °C. *Carbohydrate Polymers*, 45(4), 363–372.
- Brito, A. C. F. D., Sierakowski, M. R., Reicher, F., Feitosa, J. P. A., & Paula, R. C. M. D. (2005). Dynamic rheological study of *Sterculia striata* and karaya polysaccharides in aqueous solution. *Food Hydrocolloids*, 19(5), 861–886. <http://dx.doi.org/10.1016/j.foodhyd.2004.10.035>
- Carbonero, E. R., Gracher, A. H. P., Smiderle, F. R., Rosado, F. R., Sassaki, G. L., & Gorin, P. A. J. (2006). A β-glucan from the fruit bodies of an edible mushroom *Pleurotus eryngii* and *Pleurotus ostreatus*. *Carbohydrate Polymers*, 66, 252–257. <http://dx.doi.org/10.1016/j.carbpol.2006.03.009>
- Carbonero, E. R., Ruthes, A. C., Freitas, C. S., Utrilla, P., Gálvez, J., da Silva, E. V., et al. (2012). Chemical and biological properties of a highly branched β-glucan from edible mushroom *Pleurotus sajor-caju*. *Carbohydrate Polymers*, 90(2), 814–819. <http://dx.doi.org/10.1016/j.carbpol.2012.06.005>
- Ciucanu, I., & Kerek, F. (1984). A simple and rapid method for the permethylation of carbohydrates. *Carbohydrate Research*, 131(2), 209–217.
- Clark, A., & Ross-Murphy, S. B. (1987). Structural and mechanical properties of biopolymer gels. In A. H. Clark, & S. B. Ross-Murphy (Eds.), *Advances in polymer science* (vol. 83) (pp. 57–192). Berlin, Heidelberg: Springer. <http://dx.doi.org/10.1007/BFb0023332>
- Du, H., Hu, Q., Yang, W., Pei, F., Muinde, B., Ma, K. N., et al. (2016). Development, physicochemical characterization and forming mechanism of *Flammulina velutipes* polysaccharide-based edible films. *Carbohydrate Polymers*, 152, 214–221. <http://dx.doi.org/10.1016/j.carbpol.2016.07.035>
- Freitas, F., Alves, V. D., Carvalheira, M., Costa, N., Oliveira, R., & Reis, M. A. M. (2009). Emulsifying behavior and rheological properties of the extracellular polysaccharide produced by *Pseudomonas oleovorans* grown on glycerol byproduct. *Carbohydrate Polymers*, 78, 549–556. <http://dx.doi.org/10.1016/j.carbpol.2009.05.016>
- Goldstein, I. J., Hay, G. W., Lewis, B. A., & Smith, F. (2005). Controlled degradation of polysaccharides by periodate oxidation, reduction, and hydrolysis. *Methods in Carbohydrate Chemistry*, 5, 361–369.
- Gorin, P. A. J., & Iacomini, M. (1984). Polysaccharides of the *Cetraria islandica* and *Ramalina usnea*. *Carbohydrate Research*, 128(1), 119–132. [http://dx.doi.org/10.1016/0008-6215\(84\)85090-9](http://dx.doi.org/10.1016/0008-6215(84)85090-9)
- Gorin, P. A. J. (1981). Carbon-13 nuclear magnetic resonance spectroscopy of polysaccharides. *Advances in Carbohydrate Chemistry and Biochemistry*, 38, 13–104. [http://dx.doi.org/10.1016/S0065-2318\(08\)60309-1](http://dx.doi.org/10.1016/S0065-2318(08)60309-1)
- Hall, L. D., & Johnson, L. F. (1969). Chemical studies by ¹³C nuclear magnetic resonance spectroscopy: Some chemical shift dependencies of oxygenated derivatives. *Journal of the Chemical Society Chemical Communications*, 509–510. <http://dx.doi.org/10.1039/C29690000509>
- Heo, S., Lee, S. M., Bae, I. Y., Park, H.-G., Lee, H. G., & Lee, S. (2013). Effect of *Lentinus edodes* β-glucan-enriched materials on the textural, rheological, and oil-resisting properties of instant fried noodles. *Food Bioprocess Technology*, 6, 553–560. <http://dx.doi.org/10.1016/j.lwt.2013.10.002>
- Jansson, P. E., Kenne, L., Liedgren, H., Lindberg, B., & Lönngren, J. A. (1976). A practical guide to the methylation analysis of carbohydrates. *Chemical Communications*, 8, 1–73.
- Jones, J. K. N., & Stoodley, R. J. (1965). Fractionation using copper complexes. *Methods in Carbohydrate Chemistry*, 5, 36–38.
- Kim, J., Lee, S. M., Bae, I. Y., Park, H.-G., Lee, H. G., & Lee, S. (2011). (1→3)(1→6)-β-glucan-enriched materials from *Lentinus edodes* mushroom as a high-fibre and low-calorie flour substitute for baked foods. *Journal of the Science of Food and Agriculture*, 91, 1915–1919. <http://dx.doi.org/10.1002/jsfa.4409>
- Lapasin, R., & Prici, S. (1995). Rheology of polysaccharide systems. In R. Lapasin, & S. Prici (Eds.), *Rheology of industrial polysaccharides: Theory and applications* (pp. 250–494). Glasgow: Blackie.
- Laroche, C., & Michaud, P. (2007). New developments and prospective applications for β(1,3) glucans. *Recent Patents on Biotechnology*, 1, 59–73.
- Li, H., Lu, X., Zhang, S., Lu, M., & Liu, H. (2008). Anti-inflammatory activity of polysaccharide from *Pholiota nameko*. *Biochemistry (Moscow)*, 73(6), 669–675. <http://dx.doi.org/10.1134/S0006297908060060>
- Li, H., Zhang, B. S. M., & Ma, B. S. G. (2010). Hypolipidemic effect of the polysaccharide from *Pholiota nameko*. *Nutrition*, 26, 556–562. <http://dx.doi.org/10.1016/j.nut.2009.06.009>
- Liu, Y., Zhang, J., Tang, Q., Yang, Y., Xia, Y., Zhou, S., et al. (2016). Rheological properties of β-D-glucan from the fruiting bodies of *Ganoderma lucidum*. *Food Hydrocolloids*, 58, 120–125. <http://dx.doi.org/10.1016/j.foodhyd.2016.01.025>
- Moreno, R. B., Ruthes, A. C., Baggio, C. H., Vilaplana, F., Komura, D. L., & Iacomini, M. (2016). Structure and antinociceptive effects of β-D-glucans from *Cookeina tricholoma*. *Carbohydrate Polymers*, 141, 220–228. <http://dx.doi.org/10.1016/j.carbpol.2016.01.001>
- Neda, H. (2008). Correct name for nameko. *Mycoscience*, 49, 88–91. <http://dx.doi.org/10.1007/s10267-007-0391-3>
- Nyman, A. A. T., Aachmann, F. L., Rise, F., Balance, S., & Samuelsen, A. B. C. (2016). Structural characterization of a branched (1 → 6)-α-mannan and β-glucans isolated from the fruiting bodies of *Cantharellus cibarius*. *Carbohydrate Polymers*, 146(1), 197–207. <http://dx.doi.org/10.1016/j.carbpol.2016.03.052>
- Ren, L., Perera, C., & Hemar, Y. (2012). Antitumor activity of mushroom polysaccharides: A review. *Food & Function*, 3, 1118. <http://dx.doi.org/10.1039/c2fo10279j>
- Ren, L., Reynisson, J., Perera, C., & Hemar, Y. (2013). The physicochemical properties of a new class of anticancer fungal polysaccharides: A comparative study. *Carbohydrate Polymers*, 97, 177–187. <http://dx.doi.org/10.1016/j.carbpol.2013.04.064>
- Rodrigues, D. M. F., Freitas, A. C., Rocha-Santos, T. A. P., Vasconcelos, M. W., Roriz, M., Rodríguez-Alcalá, L. M., et al. (2015). Chemical composition and nutritive value of *Pleurotus citrinopileatus* var *cornucopiae*, *P. eryngii*, *P. salmoneus*, *Pholiota nameko* and *Hericium erinaceus*. *Journal of Food Science and Technology*, 52(11), 6927–6939. <http://dx.doi.org/10.1007/s13197-015-1826-z>
- Rodrigues, D., Freitas, A. C., Sousa, S., Amorim, M., Vasconcelos, M. W., Costa, J. P., et al. (2017). Chemical and structural characterization of *Pholiota nameko* extracts with biological properties. *Food Chemistry*, 216, 176–185. <http://dx.doi.org/10.1016/j.foodchem.2016.08.030>
- Rosado, F. R., Carbonero, E. R., Claudino, R. F., Tischer, C. A., Kemmelmeier, C., & Iacomini, M. (2003). The presence of partially 3-O-methylated mannogalactan from the fruit bodies of edible basidiomycetes *Pleurotus ostreatus* 'florida' Berk. and *Pleurotus ostreatus* Sing. *FEMS Microbiology Letters*, 221, 119–124. [http://dx.doi.org/10.1016/S0378-1097\(03\)00161-7](http://dx.doi.org/10.1016/S0378-1097(03)00161-7)
- Rout, D., Mondal, S., Chakraborty, I., Pramanik, M., & Islam, S. S. (2005). Chemical analysis of a new (1 → 3)-, (1 → 6)-branched glucan from an edible mushroom, *Pleurotus florida*. *Carbohydrate Research*, 340, 2533–2539. <http://dx.doi.org/10.1016/j.carres.2005.08.006>
- Ruthes, A. C., Carbonero, E. R., Córdova, M. M., Baggio, C. H., Santos, A. R. S., Sassaki, G. L., et al. (2013). *Lactarius rufus* (1→3), (1→6)-β-D-glucans: Structure, antinociceptive and anti-inflammatory effects. *Carbohydrate Polymers*, 94, 129–136. <http://dx.doi.org/10.1016/j.carbpol.2013.01.026>
- Ruthes, A. C., Smiderle, F. R., & Iacomini, M. (2015). D-Glucans from edible mushrooms: A review on the extraction, purification and chemical characterization approaches. *Carbohydrate Polymers*, 117, 753–761. <http://dx.doi.org/10.1016/j.carbpol.2014.10.051>
- Sassaki, G. L., Souza, L. M., Serrato, R. V., Cipriani, T. R., Gorin, P. A. J., & Iacomini, M. (2008). Application of acetate derivatives for gas chromatography mass

- spectrometry: Novel approaches on carbohydrates, lipids and amino acids analysis. *Journal of Chromatography A*, 1208(1–2), 215–222. <http://dx.doi.org/10.1016/j.chroma.2008.08.083>
- Silveira, M. L. L., Smiderle, F. R., Agostini, F., Pereira, E. M., Bonatti-Chaves, M., Wisbeck, E., et al. (2015). Exopolysaccharide produced by *Pleurotus sajor-caju*: Its chemical structure and anti-inflammatory activity. *International Journal of Biological Macromolecules*, 75, 90–96. <http://dx.doi.org/10.1016/j.ijbiomac.2015.01.023>
- Smiderle, F. R., Carbonero, E. R., Mellinger, C. G., Sasaki, G. L., Gorin, P. A. J., & Iacomini, M. (2006). Structural characterization of a polysaccharide and a β -glucan isolated from the edible mushroom *Flammulina velutipes*. *Phytochemistry*, 67, 2189–2196. <http://dx.doi.org/10.1016/j.phytochem.2006.06.022>
- Smiderle, F. R., Olsen, L. M., Carbonero, E. R., Baggio, C. H., Freitas, C. S., Marcon, R., et al. (2008). Anti-inflammatory and analgesic properties in a rodent model of a (1 $\rightarrow$ 3),(1 $\rightarrow$ 6)-linked beta-glucan isolated from *Pleurotus pulmonarius*. *European Journal of Pharmacology*, 597, 86–91. <http://dx.doi.org/10.1016/j.ejphar.2008.08.028>
- Smiderle, F. R., Olsen, L. M., Carbonero, E. R., Marcon, R., Baggio, C. H., Freitas, C. S., et al. (2008). A 3-O-methylated mannogalactan from *Pleurotus pulmonarius*: Structure and antinociceptive effect. *Phytochemistry*, 69, 2731–2736. <http://dx.doi.org/10.1016/j.phytochem.2008.08.006>
- Smiderle, F. R., Sasaki, G. L., Van Arkel, J., Iacomini, M., Wichers, H. J., & Van Griensven, L. J. L. D. (2010). High molecular weight glucan of the culinary medicinal mushroom *agaricus bisporus* is an α -glucan that forms complexes with low molecular weight galactan. *Molecules*, 15, 5818–5830. <http://dx.doi.org/10.3390/molecules15085818>
- Stanek, M., Falk, H., & Huber, A. (1998). Investigation of the branching characteristic of glycogen by means of two-dimensional ^1H and ^{13}C NMR spectroscopy. *Monatshefte für Chemie*, 129, 355–364. <http://dx.doi.org/10.1007/PL000000093>
- Synytysya, A., & Novak, M. (2014). Structural analysis of glucans. *Annals of Translational Medicine*, 2(2), 17. <http://dx.doi.org/10.3978/j.issn.2305-5839.2014.02.07>
- Wani, B. A., Bodha, R. H., & Wani, A. H. (2010). Nutritional and medicinal importance of mushrooms. *Journal of Medicinal Plants Research*, 4(24), 2598–2604. <http://dx.doi.org/10.5897/jmpr09.565>
- Xu, X., Xu, J., Zhang, Y., & Zhang, L. (2008). Rheology of triple helical lentinan in solution: Steady shear viscosity and dynamic oscillatory behavior. *Food Hydrocolloids*, 22(5), 735–741. <http://dx.doi.org/10.1016/j.foodhyd.2007.02.010>
- Xu, J. L., Zhang, J. C., Liu, Y., Sun, H. J., & Wang, J. H. (2016). Rheological properties of a polysaccharide from floral mushrooms cultivated in Huangshan Mountain. *Carbohydrate Polymers*, 139, 43–49. <http://dx.doi.org/10.1016/j.carbpol.2015.12.011>
- Yalpani, M., & Hall, L. D. (1984). Some chemical and analytical aspects of polysaccharide modifications. 3. Formation of branched-chain, soluble chitosan derivatives. *Macromolecules*, 17, 272–281.
- Yang, W., Pei, F., Shi, Y., Zhao, L., Fang, Y., & Hu, Q. (2012). Purification, characterization and anti-proliferation activity of polysaccharides from *Flammulina velutipes*. *Carbohydrate Polymers*, 88, 474–480. <http://dx.doi.org/10.1016/j.carbpol.2011.12.018>
- Zhang, Y., Liu, Z., Ng, T. B., Chen, Z., Qiao, W., & Liu, F. (2014). Purification and characterization of a novel antitumor protein with antioxidant and deoxyribonuclease activity from edible mushroom *Pholiota nameko*. *Biochimie*, 99, 28–37. <http://dx.doi.org/10.1016/j.biochi.2013.10.016>
- Zhao, H., Wang, J., & Lu, Z. (2009). Optimization of process parameters of the *Pholiota squarrosa* extracellular polysaccharide by Box-Behnken statistical design. *Carbohydrate Polymers*, 77, 677–680. <http://dx.doi.org/10.1016/j.carbpol.2009.02.013>
- Zhu, F., Bin, D., Bian, Z., & Xu, B. (2015). Beta-glucans from edible and medicinal mushrooms: Characteristics, physicochemical and biological activities. *Journal of Food Composition and Analysis*, 41, 165–173. <http://dx.doi.org/10.1016/j.jfca.2015.01.019>